

A Brief Review on Recent Advancement of Anode Materials for Biogas-Fed Solid Oxide Fuel Cells (SOFCs)

by Syuaibatul Islamiyah

Submission date: 04-Aug-2023 09:02AM (UTC+0700)

Submission ID: 2141061200

File name: 55-Article_Text-148-1-10-20221117.pdf (498.58K)

Word count: 3525

Character count: 18509

A Brief Review on Recent Advancement of Anode Materials for Biogas-Fed Solid Oxide Fuel Cells (SOFCs)

S. Islamiyah^{1*}, A Nandini¹

¹Department of Chemical Engineering, Faculty of Engineering, University of Pembangunan National Veteran Jawa Timur, 60294, Indonesia

*Corresponding e-mail: syuaibatul.tekkim@upnjatim.ac.id

Abstract. Solid Oxide Fuel Cell (SOFC) is a fuel cell technology run at high temperatures which enable internal reforming of fuel and production of high-quality by-product heat for cogeneration. The most distinguished advantage of SOFC is its excellent fuel flexibility. Biogas is one of the alternative fuels to preferable pure hydrogen. One of the important issues in operating SOFC with biogas is the formation of carbon on anode surface. Therefore, the development of coking-resistant anode materials is essential to create a high performance and stable biogas-fed SOFC. This review provides a brief survey on the recent progress of anode materials, mainly Ni-based cermet, and the modifications to prevent carbon deposition. The current situation of biogas production and utilization in Indonesia is also briefly reviewed.

Keyword: Solid Oxide Fuel Cell; Anode; Biogas

1. Introduction

The excessive use of fossil fuels is one of the main causes of Green House Gases (GHG) formation and the instability of the energy price. Various renewable energy resources are being researched as the possible substitute for fossil fuels, including solar, tidal, and wind energy, but the fluctuated production of their powers limit the energy supply. In this regard, one practical and promising method for the near future is energy conservation which is to increase the current energy conversion efficiency rather than unlimited use of intermittent alternative energy. In this regard, the fuel cells (FCs) technology is highly anticipated [1].

A fuel cell (FC) is a clean and efficient device to convert the chemical energy of fuels such as hydrogen and hydrocarbons into electrical energy with very high efficiency (>60%) compared to the established technology of the internal combustion engine (ICE). One main advantage of fuel cells is their fuel flexibility. Because of its high reactivity for the electrochemical anode reaction and the fact that its oxidation produces water, hydrogen is preferred in many types of fuel cells. However, since hydrogen does not naturally exist as a gaseous fuel, it must often be produced from a fuel source that is readily available in the area for viable fuel cell systems to function [2]. To address the problems associated with hydrogen production, storage, and transport, alternative fuels are considered.

Biogas is promising alternatives among available fuel options due to its accessibility, affordability, and potential as a distributed energy source [3]. Anaerobic digestion (AD) is a common method used in rural communities of developing country to produce biogas, which can then be used as a source of energy. However, because of the high amount of CO₂ dilution and the fuel's low calorific value, it cannot be used in conventional burners or heat engines [4]. Solid-oxide fuel cells (SOFCs), with its fuel flexibility, can use biogas directly and with little pre-treatment. SOFCs employ both CH₄ and CO₂ contained in biogas to create a syngas (CO+ H₂) combination with a higher energy content, which further are oxidized to produce electricity, via internal dry reforming [5].

Since SOFCs fed by biogas are still in their early-stage research compared to SOFCs fed by pure hydrogen, extensive research is necessary to explore and further develop new materials that enable a stable operation with high output. This review aims to summarize the recent development of anode materials used in biogas fed SOFC and discuss the problem associated when using biogas as fuel in SOFCs, as well as present solutions offered by researchers. In addition, the feasibility of integrating SOFC system to electricity generation in Indonesia is also concluded.

2. Biogas in Indonesia

Biogas is a fuel derived from biomass source commonly through anaerobic digestion (AD). The digestion of organic material in biomass involving microbes and occurs in four steps: hydrolysis, acidogenesis, acetogenesis, and methanogenesis [6]. Methane, carbon dioxide, and trace amounts of nitrogen and hydrogen make up the majority of biogas [7]. It can be used to generate electricity and heat as well as to power a gaseous car. By using biogas, an effort is made to both reduce GHG emissions and increase the economic value of waste as a source of energy [8].

Figure 1 illustrates how various biogas applications provide flexible means of reducing the necessary energy for the industrial or social sectors. The primary uses of biogas are in combined heat and power (CHP) facilities, hydrogen production facilities, and advanced energy systems like fuel cells. [9].




Figure 1. The overview of biogas utilization

The biogas contains 55 to 70% methane, 30 to 45% carbon dioxide, and other trace gases such as oxygen, carbon monoxide, and hydrogen sulfide [10]. To obtain biogas from the biomass source, the organic waste should be placed in an oxygen-free area. The organic matter in the waste will break down and create biogas. Because the carbon in biogas is derived from organic waste that has fixed atmospheric carbon dioxide, it is considered as carbon neutral energy source. Organic trash is also highly sustainable because it will continue to grow and be available as long as the humankind exists.

Animal farms, municipal solid waste, agricultural residues, industrial sludge, and wastewater treatment plants are all sources of the numerous feedstocks used to produce biogas. Muzenda (2014) identified suitable biomass for biogas production (i.e. food waste, manure, crop residue, abattoir waste, and stillage). Food waste was shown to have a high potential as a biogas feed source since it contains proteins, lipids, carbs, and trace components that encourage a balanced process. Biomass with a high fat content has the greatest potential for biogas production [11].

By 2025, the Indonesian government plans to incorporate 23% share of renewable energy in their energy supply. In 2015, 16,000 biogas plants had been installed across ten provinces in Indonesia [12]. Most biogas production case studies in Indonesia are currently conducted on a small scale with animal waste as a potential feedstock. Various feedstocks, from municipal solid waste to human excreta, were then also being explored to evaluate the viability of producing biogas in Indonesia [13–16]. The biogas produced is concentrated on being utilized directly for home activities, such as cooking and water heating, as the majority of biogas facilities are located in rural regions. There are initiatives, however, to improve the quality of the biogas generated by these facilities using purifying techniques, such as pressurized gas scrubbing [17].

3. Solid Oxide Fuel Cell (SOFC)

SOFC is a fuel cell technology that often runs at high temperatures. It is excellent for use in big, high-power applications, including major industrial facilities and power plants. SOFC systems typically run at very high temperatures (600–1000°C) and employ solid ceramics as electrolytes. The high operating temperature allows internal reformation of the fuel, which also encourages quick electrocatalytic reactions with base metals and generates high-quality by-product heat for cogeneration. This kind of fuel cell's efficiency can increase to 60%.

Three primary parts make up a solid oxide fuel cell: anode, cathode, and a dense electrolyte. The operating principles of a typical oxygen-ion conducting electrolyte SOFC are depicted in Figure 2. The anode receives fuel, such as H₂ or hydrocarbon, and the cathode receives oxygen from the air. At the cathode side, oxygen is converted to O²⁻ and transferred via the electrolyte to the anode in order to produce electricity. By way of an external pathway, the free electrons generated by the oxidation reaction at the anode then move to the cathode. The SOFC obviously does not burn fuel, which automatically prevents the Carnot cycle, which is why it has a higher electrical efficiency than traditional power generators.






Figure 2. The schematic working principle of SOFC

The reduction of hydrogen and oxidation of oxygen at the anode and cathode sides respectively are shown below [18]



When using biogas, the main reactions are steam reforming and dry reforming as shown below



In addition to dry reforming reactions, there are other reaction paths, such as the water gas shift reaction.



The water-gas shift equilibrium can be pushed in either direction depending on the reaction conditions. The predominant reactions in fuel cell systems depend on the temperatures, gas concentrations, and system configuration [19]

Biogas are oxidized with oxide ions at the anode in SOFC. Strong electronic conductivity and higher resistance to carbon deposition are especially important requirements for the anode material. Recently, various research projects have shifted their focus to the direct use of biogas in SOFC systems, and as a result, attention has been put into developing coking-resistant anode materials. The majority of the anode materials utilized in biogas-fed SOFC today are nickel-based anodes. The following section will discuss more details on anode materials used in biogas fed SOFCs to date.

4. Anode Materials used for biogas fueled SOFC

Most current research on SOFC powered by biogas focuses on Ni-based anodes. This is due to Ni's dual function, which is a good catalyst for producing C-C bonds and breaking C-H bonds. However, coking resistance has to be improved with specific, focused modifications. [20]. Nickel oxide-YSZ (NiO-YSZ) or nickel oxide-GDC (NiO-GDC) are commonly used composite materials in state-of-the-art SOFC. This type of electrodes is called composite electrode and mixed ionic and electronic conducting materials (MIECs). The mixed conductivities are especially beneficial since they can facilitate more triple-phase boundaries (TPBs) formation, an area in which the fuel, anode and electrolyte come in contact. These advantages of composite electrodes enhance catalytic processes generally, as well as the lifetime and electrochemical performance of the fuel cell stack at the device level [9–11]. However, Ni-YSZ is prone to coking and deactivation by other pollutants when hydrocarbon is used as fuel in SOFC. Researchers have been exploring various scenarios to suppress the coking on the anode's surface.

Ma et al. infiltrated $\text{BaZr}_{0.1}\text{Ce}_{0.7}\text{Y}_{0.1}\text{Yb}_{0.1}\text{O}_{3-\delta}$ (BCZYYb) into Ni-YSZ anode. This strategy significantly enhanced the electrochemical performance of the cells. A maximum power density of 1.43 W cm^{-2} at 750°C was yielded and the cell remained stable after 50 hours operation. Different current loads were used to investigate the most common reactions, and the result suggested that reforming methane without carbon formation was the dominant reaction [19]. The modification of Ni-YSZ with TiO_2 also shows improved peak power density at 850°C with less carbon deposition after 40 h operation. The TiO_x powder that is reduced under high-temperature infrared light excitation produces hydroxyl radical, and it is believed to be the possible factor for the modified anode's high activity and resistance to carbon deposition [24].

Another anode material that has been extensively researched is Ni-GDC. Saadabadi et al. investigated a Ni-GDC anode under different ratios of CH_4/CO_2 , or commonly annotated as (R). The study reveals that the cell performance is dependent on R value. When $R \leq 1$, a stable cell performance has been attained, and when $R > 1$, coking is noticed. $R = 1$ produced the best results because there was the least amount of deterioration and the most amount of power generation [25]. To inhibit the graphitic carbon deposition, Au was incorporated into Ni-GDC. The result shows although carbon deposit was observed, it did not hinder the electrochemical performance of the cell under closed-circuit condition. The reactions involved in preventing carbon deposition under closed-circuit operation are as follows [26]:



Ni-ScSZ is also actively researched as an alternative to Ni-YSZ anode. The experiment by a research group in Kyushu University reveals severe coking was observed when using actual biogas as a fuel. The H₂S contamination of the actual biogas might lead to this carbon formation. They found that the air addition to the actual biogas could lower the possibility of carbon deposition and allow SOFC to operate more steadily [27]. The coke formation is less expected when doping tin (Sn) to Ni-ScSZ anode. However, while the electrochemical performance of the cell improved, higher deposited carbon was detected on the doped anode compared to the pristine one. Although the carbon deposition did not impede the electrochemical performance, it can further lead to breaking the anode, so it should be prevented. [28]. Other anode materials used to operate biogas fed SOFC is listed in Table 1.

Table 1. The list of anode materials used in biogas fed SOFC

Anode	Operating Temperature (°C)	Fuel	Ref.
BaZr _{0.1} Ce _{0.7} Y _{0.1} Yb _{0.1} O _{3-δ} (BCZYYb) infiltrated Ni-YSZ	750-850	simulated biogas (CH ₄ /CO ₂ /H ₂ O/H ₂ /CO=36/36/20/4/4%)	[19]
TiO ₂ modified Ni-YSZ	850	simulated biogas (R=2.3)	[24]
Ni-GDC	800-900	simulated biogas (R= 0.6-1.5)	[25]
Ni(Au)-GDC	640	Simulated biogas (R=1)	[26]
NMO coated GDC and NiO	500-700	wet CH ₄	[29]
Cu impregnated NiO-GDC	610	simulated biogas	[30]
Ni-ScSz	800	actual biogas	[27]
Sn-Ni-ScSz	750	dry biogas	[28]
Ni-CGO	400-800	simulated biogas (R=1)	[31]
Co-Ni-CGO			
Cu-Ni-CGO			
Mo-Ni-CeO ₂	750	simulated biogas (CH ₄ /CO ₂ /H ₂ =70/25/5%)	[32]

5. Conclusion

In terms of versatility to operate with diverse fuel combinations, SOFC systems are promising technologies for electricity generation. Biogas is a intriguing fuel option that should be researched. Furthermore, the existing high CO₂ concentration available could favor direct internal methane reforming. The potential to use SOFC in generating electricity from biogas in Indonesia is huge. The utilization of biogas in Indonesia now is mostly for household purposes such as cooking. Learning from Malaysia, integrating SOFC into anaerobic digester could yield 76.95% higher performance than the conventional biogas-based electricity generation.

To date, Ni-based anodes are still the most extensively researched with some modifications to hinder the coke formation. The extensive development of anode material for biogas-fed SOFC has promised more possibilities in realizing the application of SOFC technology for generating electricity, especially in rural areas. SOFC is a complex system, so more research must be carried out to understand all reactions and mechanisms involved to yield higher power output. In addition, a study on the possible

application of biogas-fed SOFC in Indonesia could be one of the areas of interest since there needs to be more studies in this area.

References

- [1] Bellino M G, Sacanell J G, Lamas D G, Leyva A G and Walsöe De Reca N E 2007 High-performance solid-oxide fuel cell cathodes based on cobaltite nanotubes *J. Am. Chem. Soc.* **129** 3066–7
- [2] Moseley P T 2001 *Fuel Cell Systems Explained* vol 93
- [3] Yentekakis I V. and Goula G 2017 Biogas management: Advanced utilization for production of renewable energy and added-value chemicals *Front. Environ. Sci.* **5**
- [4] Huang J and Crookes R J 1998 Assessment of simulated biogas as a fuel for the spark ignition engine *Fuel* **77** 1793–801
- [5] Jones C M, Persky J and Datta R 2017 Exploring Conditions That Enhance Durability and Performance of a Tubular Solid Oxide Fuel Cell Fed with Simulated Biogas *Energy and Fuels* **31** 12875–92
- [6] Kapoor R, Ghosh P, Tyagi B, Vijay V K, Vijay V, Thakur I S, Kamyab H, Nguyen D D and Kumar A 2020 Advances in biogas valorization and utilization systems: A comprehensive review *J. Clean. Prod.* **273**
- [7] Shafie S M, Nu'man A H and Yusuf N N A N 2021 Biogas to Fuel Cell State of The Art: A Review *J. Adv. Res. Fluid Mech. Therm. Sci.* **86** 87–104
- [8] Hosseini S E and Wahid M A 2013 Feasibility study of biogas production and utilization as a source of renewable energy in Malaysia *Renew. Sustain. Energy Rev.* **19** 454–62
- [9] Abanades S, Abbaspour H, Ahmadi A, Das B, Ehyaei M A, Esmailion F, El Haj Assad M, Hajilounezhad T, Jamali D H, Hmida A, Ozgoli H A, Safari S, AlShabi M and Bani-Hani E H 2022 A critical review of biogas production and usage with legislations framework across the globe *Int. J. Environ. Sci. Technol.* **19** 3377–400
- [10] Deublein D and Steinhauser A 2010 Biogas from Waste and Renewable Resources: An Introduction, Second Edition *Biogas from Waste Renew. Resour. An Introd. Second Ed.*
- [11] Muzenda E 2014 Bio-methane generation from organic waste: A review *Lect. Notes Eng. Comput. Sci.* **2** 647–52
- [12] Roubík H and Mazancová J 2020 Suitability of small-scale biogas systems based on livestock manure for the rural areas of Sumatra *Environ. Dev.* **33** 100505
- [13] Hendroko Setyobudi R, Krido Wahono S, Gamawati Adinurani P, Wahyudi A, Widodo W, Mel M, Adhi Nugroho Y, Prabowo B and Liwang T 2018 Characterisation of Arabica Coffee Pulp - Hay from Kintamani - Bali as Prospective Biogas Feedstocks *MATEC Web Conf.* **164**
- [14] Sitompul J P, Bayu A, Soerawidjaja T H and Lee H W 2012 Studies of Biogas Production from Green Seaweeds *Int. J. Environ. Bioenergy Int. J. Environ. Bioener* **2012** 132–44
- [15] Andriani D, Wresta A, Saepudin A and Prawara B 2015 A review of recycling of human excreta to energy through biogas generation: Indonesia case *Energy Procedia* **68** 219–25
- [16] Anshar M, Ani F N and Kader A S 2014 The energy potential of municipal solid waste for power generation in Indonesia *J. Mek.* **37** 42–54
- [17] Sinaga N, Nasution S B and Mel M 2018 Process optimization of biogas production from palm oil mill effluent: A case study of a crude palm oil factory in Muaro Jambi, Indonesia *J. Adv. Res. Fluid Mech. Therm. Sci.* **49** 155–69
- [18] Saadabadi S A, Thallam Thattai A, Fan L, Lindeboom R E F, Spanjers H and Aravind P V. 2019 Solid Oxide Fuel Cells fuelled with biogas: Potential and constraints *Renew. Energy* **134** 194–214
- [19] Ma J, Jiang C, Connor P A, Cassidy M and Irvine J T S 2015 Highly efficient, coking-resistant SOFCs for energy conversion using biogas fuels *J. Mater. Chem. A* **3** 19068–76
- [20] Wang Z, Li Y and Schwank J W 2014 Evaluation of Ni/SDC as anode material for dry CH₄

- fueled Solid Oxide Fuel Cells *J. Power Sources* **248** 239–45
- [21] Li Z P, Mori T, Auchterlonie G J, Zou J and Drennan J 2011 Superstructure formation and variation in Ni-GDC cermet anodes in SOFC *Phys. Chem. Chem. Phys.* **13** 9685–90
- [22] Aruna S T, Muthuraman M and Patil K C 1998 Synthesis and properties of Ni-YSZ cermet: Anode material for solid oxide fuel cells *Solid State Ionics* **111** 45–51
- [23] Koide H, Someya Y, Yoshida T and Maruyama T 2000 Properties of Ni/YSZ cermet as anode for SOFC *Solid State Ionics* **132** 253–60
- [24] Gu D, Zhang G and Zou J 2021 High temperature thermo-photocatalysis driven carbon removal in direct biogas fueled solid oxide fuel cells *Chinese Chem. Lett.* **32** 3548–52
- [25] Saadabadi S A, Illathukandy B and Aravind P V 2021 Direct internal methane reforming in biogas fuelled solid oxide fuel cell; the influence of operating parameters *Energy Sci. Eng.* **9** 1232–48
- [26] Yentekakis I V. 2006 Open- and closed-circuit study of an intermediate temperature SOFC directly fueled with simulated biogas mixtures *J. Power Sources* **160** 422–5
- [27] Shiratori Y, Ijichi T, Oshima T and Sasaki K 2010 Internal reforming SOFC running on biogas *Int. J. Hydrogen Energy* **35** 7905–12
- [28] Arifin N A, Troskialina L, Shamsuddin A H and Steinberger-Wilckens R 2020 Effects of Sn doping on the manufacturing, performance and carbon deposition of Ni/ScSZ cells in solid oxide fuel cells *Int. J. Hydrogen Energy* **45** 27575–86
- [29] Li Q, Wang X, Li C, Yang X, Jia L and Li J 2022 A direct CH₄ metal-supported solid oxide fuel cell with an engineered Ni/Gd-doped CeO₂ anode containing Ni and MnO nanoparticles *Compos. Part B Eng.* **229** 2–8
- [30] Patil S P, Jadhav L D and Chourashiya M 2022 Investigation of quality and performance of Cu impregnated NiO-GDC as anode for IT-SOFCs *Open Ceram.* **9** 100230
- [31] Cesario M R, Souza G S, Loureiro F J A, Araújo A J M, Grilo J P F, Aouad S, Tidahy H L, Macedo D A, Fagg D P, Gennequin C and Abi-Aad E 2021 Synthesis of Co–Ni and Cu–Ni based-catalysts for dry reforming of methane as potential components for SOFC anodes *Ceram. Int.* **47** 33191–201
- [32] Escudero M J, Maffiotte C A and Serrano J L 2021 Long-term operation of a solid oxide fuel cell with MoNi–CeO₂ as anode directly fed by biogas containing simultaneously sulphur and siloxane *J. Power Sources* **481** 229048

A Brief Review on Recent Advancement of Anode Materials for Biogas-Fed Solid Oxide Fuel Cells (SOFCs)

ORIGINALITY REPORT

16%

SIMILARITY INDEX

10%

INTERNET SOURCES

13%

PUBLICATIONS

%

STUDENT PAPERS

PRIMARY SOURCES

1

pubs.rsc.org

Internet Source

2%

2

www.akademiabaru.com

Internet Source

2%

3

Nur Izzah Hamna Abdul Aziz, Marlia M. Hanafiah, Mohamed Yasreen Mohamed Ali. "Sustainable biogas production from agrowaste and effluents – A promising step for small-scale industry income", Renewable Energy, 2018

Publication

1%

4

link.springer.com

Internet Source

1%

5

Wei Wang, Chao Su, Yuzhou Wu, Ran Ran, Zongping Shao. "Progress in Solid Oxide Fuel Cells with Nickel-Based Anodes Operating on Methane and Related Fuels", Chemical Reviews, 2013

Publication

1%

6	www.researchgate.net Internet Source	1 %
7	Shiratori, Y.. "Internal reforming SOFC running on biogas", International Journal of Hydrogen Energy, 201008 Publication	1 %
8	"Fuel Cells and Hydrogen Production", Springer Science and Business Media LLC, 2019 Publication	1 %
9	patents.google.com Internet Source	1 %
10	scholarcommons.sc.edu Internet Source	<1 %
11	Ma, Jianjun, Cairong Jiang, Paul A. Connor, Mark Cassidy, and John T. S. Irvine. "Highly efficient, coking-resistant SOFCs for energy conversion using biogas fuels", Journal of Materials Chemistry A, 2015. Publication	<1 %
12	María José Escudero, Conrado Valero, Miguel Ángel Cauqui, Daniel Goma, María Pilar Yeste. "Ni-Ce-ZrO ₂ system as anode material for direct internal reforming biogas solid oxide fuel cells", Fuel, 2022 Publication	<1 %

13	www.freepatentsonline.com Internet Source	<1 %
14	Sarika P. Patil, L.D. Jadhav, Muralidhar Chourashiya. "Investigation of quality and performance of Cu impregnated NiO-GDC as anode for IT-SOFCs", Open Ceramics, 2022 Publication	<1 %
15	"Advanced Intelligent Systems for Sustainable Development (AI2SD'2019)", Springer Science and Business Media LLC, 2020 Publication	<1 %
16	vdocuments.net Internet Source	<1 %
17	M.J. Escudero, C.A. Maffiotte, J.L. Serrano. "Long-term operation of a solid oxide fuel cell with MoNi-CeO ₂ as anode directly fed by biogas containing simultaneously sulphur and siloxane", Journal of Power Sources, 2021 Publication	<1 %
18	Seyed Ehsan Hosseini, Mazlan Abdul Wahid. "Pollutant in palm oil production process", Journal of the Air & Waste Management Association, 2013 Publication	<1 %
19	Steven McIntosh, Raymond J. Gorte. "Direct Hydrocarbon Solid Oxide Fuel Cells", Chemical Reviews, 2004	<1 %

20

de.slideshare.net

Internet Source

<1 %

21

docplayer.net

Internet Source

<1 %

22

keep.lib.asu.edu

Internet Source

<1 %

23

mdpi-res.com

Internet Source

<1 %

24

www.mdpi.com

Internet Source

<1 %

25

www.nature.com

Internet Source

<1 %

26

"Modeling, Design, Construction, and Operation of Power Generators with Solid Oxide Fuel Cells", Springer Science and Business Media LLC, 2018

Publication

<1 %

27

Elisabeth Rianawati, Saut Sagala, Ichsan Hafiz, Johannes Anhorn et al. "The potential of Biogas in Energy Transition in Indonesia", IOP Conference Series: Materials Science and Engineering, 2021

Publication

<1 %

28

"Affordable and Clean Energy", Springer Science and Business Media LLC, 2021

<1 %

29

Ayhan Demirbas. "Chapter 7 Fuel Cells",
Springer Science and Business Media LLC,
2009

Publication

<1 %

30

Toshiyuki Mori, Roger Wepf, San Ping Jiang.
"Future prospects for the design of 'state-of-
the-art' solid oxide fuel cells", Journal of
Physics: Energy, 2020

Publication

<1 %

31

scholarsmine.mst.edu

Internet Source

<1 %

Exclude quotes On

Exclude matches Off

Exclude bibliography On